



W-Ni-Fe

composition
after sintering

W%	Ni%	Fe%
95.5-96.5	2.0-2.8	1.2-2.0

Characteristic
Properties

	as sintered
Density\g/cm ³	≥18.25
Yield Strength R _{P0.2} \Mpa	≥600
Ultimate Tensile Strength\Mpa	≥900
Elongation\%	≥10
Hardness\HRC	25-35
magnetism	have