



W-Ni-Cu-Co

composition
after
sintering

W%	Ni%	Cu%	Co%
95.5-96.5	2.5-3.0	0.5-1.0	0.3-0.7

Characteristic
Properties

	as sintered
Density\g/cm ³	≥18.30
Yield Strength R _{P0.2} \Mpa	≥600
Ultimate Tensile Strength\Mpa	≥900
Elongation\%	≥7
Hardness\HRC	27-35
magnetism	Not have