



YG15

composition
after sintering

WC%	Co%
85	15

Characteristic
Properties
(Typical values)

	as sintered
Density\g/cm ³	14.0
Hardness\HRA	≥86.5
magnetic saturation\%	14.0
magnetic coercivity\kA*m- 1	7.5
Flexure strength\Mpa	2700